

PRO MIX AIRLESS F



Product Description

PRO MIX AIRLESS F is a fine, ready-mix filler for finishing indoor surfaces. Suitable for a wide variation of backgrounds e.g. plasterboards, plasters and concrete. Air-drying

Advantages

PRO MIX AIRLESS F is recommended for Q3- Q4. For this, no priming is necessary before painting. This material is highly refined and thus easy to apply (no peeling). Using buckets, no material has to be thrown away, thus saves costs of material. When finishing work, before closing the bucket, cover material with some water. PRO MIX AIRLESS F is a white filler, thus saves expenses for painting. It is easy to sand, has got excellent bond and good crack resistance characteristics, always offered in perfect consistency.

Application

PRO MIX AIRLESS F can be used directly from the bucket or with some mixing before use. Clean water could be added if it's necessary. Excessive dilution increases shrinkage and retards drying. Add water in increments to avoid over-thinning. It

is recommended that not more than 1.0 litre is added per 25kg bucket.

PRO MIX AIRLESS F is recommended as finisher on the top of every Joint Filler.

For sanding it is recommended to use a 220 paper when manual and a 120 with a machine. A primer (Ri-Kombigrund) is recommended prior to a wallpaper application. PRO MIX AIRLESS F can be used by hand and by Airless application. Application thickness is up to about 3mm.

The drying time (overnight) depends on climatic conditions. Do not mix with other materials. Cleaning with clean water.

Site Conditions

Air-, material and background temperature have to be above 8°C. The background has to be solid, clean, dust free and dry.

Handling

Q1: Fill the joints and deduct excessive material from surface. Bed Rigips paper tape into the joint and cover it with additional material (e.g. use Rifino Top)

Q2: If necessary remove excessive material from joints.

Once material set, cover the existing joint with additional material (e.g. use Rifino Top). This is necessary as long as any transitions exist. Once the material dried, sand it if necessary.

Q3: Cover full surface by thin strength of coating and that followed remove material to close the pores.

Q4: Cover full surface with up to 3mm strength of coating.

Quality Standard

Q3 – Q4

EN-Classification

CE 3A – EN 13963 – A2– NPD

Product Data

Application-thickness	up to 3 mm
Working-time	app. 3 months
Drying time	App. 24 hours
Consumption	Surface: app. 1,6 kg/m ² /mm
Fire resistance	A2

Information

Package-size	25 kg
Storage	Shelf life: Ensure stock rotation and use within 12 months of the marked date. Protect from freezing - store between 2°C and 30°C

For further information please contact

Saint-Gobain Rigips Austria GesmbH
Wiener Neustädter Straße 63
A-2734 Puchberg / Schneeberg

Tel. +43 (0) 2636 / 2203-0
Fax +43 (0) 2636 / 2206-625

www.rigips.com



Handling



Working time



Application thickness



Consumption



Quality standard

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.