

Rigips ALABASTERGIPS



Product Description

ALABASTERGIPS is a multiphase gypsum ($\text{CaSO}_4 \cdot n \text{H}_2\text{O}$; $n = 0, \frac{1}{2}, 2$), produced from naturally occurring gypsum mineral.

Colour: whitely

Application

ALABASTERGIPS is used for stucco, plaster profiles, repairs, finishing layer on walls and ceilings (hard smoothing) and for manufacturing of models.

Site Conditions

Air-, material and background temperature have to be above $+5^\circ\text{C}$. The background has to be solid, clean, dust free and dry.

Preparation

Remove loose material, dirt, dust etc. The repairing area should be pre-wetted.

Handling

ALABASTERGIPS can be handled about 15 minutes and it is getting hard within 20 minutes. Mix approx. 1,5 kg gypsum into 1 litre water. Use only absolutely clean vessels and

tools. Gypsum residues can change the setting time. You have always to sprinkle the BAUGIPS into the mixing water, never vice versa.

You have to allow ALLABASTERGIPS to soak in for about 1 minute and then mix it.

Anchors can be used at the earliest after 24 hours.

Technical Data

The stated technical data are typical figures.

Usage powder:
130 – 160 g/100 ml water
Initial set: ≥ 8 min
Final set: ≤ 45 min
pH-value: 7
Sieve residue: R 200 μm : max. 0,5%
Flexural strength: ≥ 5 N/mm²
Compressive strength: ≥ 15 N/mm²

Changes of the ratio powder to water will affect the product performance, especially the setting time and strength.

As gypsum products are not moisture-resistant, therefore they are not recommended for usage outdoors and at excessive moisture.

Absorption of moisture can result in changes to physical properties including a shortening of setting time.

EN-Classification

 EN 13279-1 A /A1

Product Data


Mixing ratio	app. 1,5 kg / 1 L water
Working time	app. 15 – 20 min.
Fire resistance	A1
Vapour diffusion resistance	$\mu = 10$
Flexural- and tensile bond strength	According to EN 13279-1
Package-size	25 kg
Storage	
Shelf life: Ensure stock rotation and use within 12 months of the marked date. Use unsealed bags within 3 months. Protect from freezing - store between $+2^\circ\text{C}$ and $+30^\circ\text{C}$.	

For further information please contact:

Saint-Gobain Rigips Austria GesmbH
Wiener Neustädter Straße 63
A-2734 Puchberg / Schneeberg
Tel. +43 (0) 2636 / 2203-0
Fax +43 (0) 2636 / 2206-625
www.rigips.com



Application



Handling



Working time

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.