

Rigips RIMANO 3-6



Product Description

RIMANO 3-6 is a manual gypsum plaster with specific adhesion properties for walls and ceilings.

Ingredients: dry mixture of plaster and adhesive active additives.

Advantages

RIMANO 3-6 is an easy workable gypsum plaster. It has excellent adhesive properties. There is a low consumption by layer thickness of minimum 3 mm. Suitable as a background for paints, varnishes and wallpaper.

Application

RIMANO 3-6 is a fine adhesive smoothing plaster for relatively flat, weak to strong suction backgrounds in a thin-application thickness, e.g. smooth-formed concrete surfaces or aerated concrete. RIMANO 3-6 may be applied on smooth concrete surfaces, but only with Rikombi-Kontakt as a bonding agent. It is suitable for filling cracks, holes and closing joints, but not for tiling.

Site Conditions

Air-, material and background temperature have to be above +5°C. The background has to be solid, clean, dust free and dry. Assure that the substrate is clean and dry and free of moulding oil remainders.

Preparation


For high suction backgrounds use Rikombi-Grund for priming. (e.g. aerated concrete) On smooth concrete backgrounds use it only with Rikombi-Kontakt as a bonding agent (e.g. concrete).

Handling

Add approx. 1,2 kg RIMANO 3-6 into 1 litre of clean water and allow to soak in for around 5 minutes. Then mix either by hand or with an electric drill with mud paddle (low speed) till the mixture is lump-free.

Apply the material in the requested application thickness. If the plaster starts to set, then recut it. After the surface is sufficiently solid, then smooth the surface with a trowel. Make further layers after complete drying out.

EN-Classification

 EN 13279-1- A1- B1/20/2

Product Data

Mixing ratio	app. 1,2 kg / 1 L water
Working-time	app. 60 min.
Application-thickness	3 – 6 mm
Consumption	app. 0,9 kg/m ² /mm
Fire resistance	A1
Vapour diffusion resistance	$\mu = 10$
Flexural- and tensile bond strength	According to EN 13279-1
Package size	5 kg / 25 kg
Storage: Shelf life: Ensure stock rotation and use within 12 months of the marked date. Use unsealed bags within 3 months. Protect from freezing - store between +2°C and +30°C.	

For further information please contact:

Saint-Gobain Rigips Austria GesmbH
Wiener Neustädter Straße 63
A-2734 Puchberg / Schneeberg

Tel. +43 (0) 2636 / 2203-0
Fax +43 (0) 2636 / 2206-625

www.rigips.com

Indoor



Application

Manual



Handling

app. 60 min



Working time

3 – 6 mm



Application thickness

ca.0,9 kg/m²/mm



Consumption

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.